



0013

YOUR PARTNER IN MATERIALS AND TECHNOLOGY



Queens Road Penkhull
Stoke-on-Trent ST4 7LQ
Tel: +44 (0) 1782 764444
Fax: +44 (0) 1782 412331
E-mail: info@ceram.com
http://www.ceram.com

PHYSICAL TESTING REPORT

Preform Technologies Ltd
Centurion Way Business Park
Alfreton Road
Derby
DE21 4AY

This report is a supplement to
the report issued on 11.02.09 for
CERAM Reference (09157) - 696
for Determination of Thermal
Conductivity.

FAO: S Whalley

REPORT OF TESTS ON: Knitted EC.R Glass

Your Reference: Ref 1296 1200gsm 12mm

CERAM Reference: (09157)-696 /Supplement Report

Date Reported 26-Feb-2009 Order Number: SW171208

Date Logged 09-Jan-2009 Date(s) of Test(s): 06-Feb-2009 to 09-Feb-2009

Determination of Thermal Conductivity

BS 1902: Section 5.5: 1991

Table with 6 columns: No., Hot Face Temperature (°C), Cold Face Temperature (°C), Mean Temperature (°C), Thermal Conductivity (W/m.K), Heat Flow (W). Row 1: 1, 805, 228, 517, 0.35, 15.920

Bulk Density of Sample: 110 kg/m³

Direction that heat flow measurements were taken through: 70 mm

Bulk density of the sample was determined by weight and dimensions.

End of Test Report

S Hall

Authorised Signatory



INVESTOR IN PEOPLE